

XYSIL®200

Hydrophilic Fumed Silica

TECHNIQUE DATA SHEET

XYSIL[®] **200** is a hydrophilic Fumed Silica with a specific surface area of 200m²/g, and also known as Synthetic, Amorphous Silica, manufactured by

a continuous flame hydrolysis process of silicon tetrachloride.

Characteristic physico-chemical data

Properties	Units	Guarantee value	Standardization
Specific surface area (BET)	m²/g	200±25	GB/T10722
pH-value (in 4% dispersion)		3.8-4.5	GB/T1717
Loss on drying, ex works(2h @ 105°C)	wt%	<1.5	GB/T5211.3
Loss on ignition(2h @ 1000,based on material dried for 2h @ 105℃)	wt%	<2.5	GB/T20020
Sieve residue (45µm)	%	<0.05	GB/T5211.14
SiO₂ content (based on the substance heated at 1000°C for 2 h)	wt%	>99.8	GB/T20020
Tamped density (based on material dried for 2h @ 105°C)	g/L	25~60	GB/T5211.4
Carbon content (based on material dried for 2h @ 105℃)	wt%	<0.2	GB/T20020
Appearance	Fine,White,Amorphous Powder		

At time of packaging.

Applications and Properties

Application:

- > RTV Silicone Sealant, HTV Silicone Rubber
- Paints and Coatings, Ink, Pigment
- Unsaturated polyester resins
- Adhesive & Sealant
- > Thermal insulation material, Vacuum Insulation Panel
- Composites& PVC, Storage Battery

Functions:

- > Rheology and thixotropy Control of of liquids, binders, polymers, etc.
- Used as anti-settling, thickening, anti-sagging agent
- > Free Flow and Suspension for Powder
- > Reinforcement in Silicone Rubber

Packaging and Storage

XYSIL® 200 is packaged in multiple layer kraft paper 10kg bags or 180Kg FIBCs on pallet, and should be stored in the original packaging in dry storage areas for protecting the material from volatile substance, and should be used in two years after production.

Transportation:

20'GP: 1800KG, 10 pallets, 180KG/pallet. 40'GP: 3600KG, 20 pallets, 180KG/pallet. 40'HQ: 4000KG, 20 pallets, 200KG/pallet. Road Transportation: by requirement

Registrations(substance or product components)

Chemical Name	CAS NO.	REACH(EU)	KKDID	K-REACH	TSCA	Customs Tariff Number
Silicon Dioxide	112945-52-5, 7631-86-9	Registered	Registered	Registered	Registered	281122(Internet); 2811229000(China)

This information is supplied on basis of our best knowledge, as a convenience and for information purposes only. We disclaim any warranty and liability whatsoever as to accuracy and completeness of such information as well as to the potential infringement of any proprietary rights.