

Technical Data Sheet

Ferro Manganese

ACM-FM01

ACM-SC01 Analysis			
Item	Indicator	Standard Valve(%)	
1	Mn 🚽	76-78	
2	Si	2 Max	
3	С	6-8	
4	P	0.25 Max	
5	S	0.03 Max	
3	3	0.05 Max	

Size distribution			
10-80 mm			
(90%min)			

Storage: Stored in the dry and ventilated inside storeroom, prevent direct sunlight, slightly pile and put down.

اى سى ام جلوبال لتجارة الخامات و المواد الاولية شذم.م ACM Global Raw Material Trading L.L.C Office 1503, Emirates Concorde Building, Office Towers, Al Maktoum Street, Deira, Dubai, UAE www.acm-gtl.com o0971505730551 info@acm-gtl.com